



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>A61K 31/785</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 95/24908</b> <b>(43) International Publication Date:</b> 21 September 1995 (21.09.95)
<b>(21) International Application Number:</b> PCT/US95/03040 <b>(22) International Filing Date:</b> 9 March 1995 (09.03.95) <b>(30) Priority Data:</b> 214,372 17 March 1994 (17.03.94) US <b>(71) Applicants:</b> THE UNITED STATES OF AMERICA, represented by THE SECRETARY, DEPARTMENT OF HEALTH AND HUMAN SERVICES National Institutes of Health [US/US]; Office of Technology Transfer, Box OTT, Bethesda, MD 20892-9902 (US). COMEDICUS, INC. [US/US]; 3050 Jamestown Road, Long Lake, MN 55356 (US). <b>(72) Inventors:</b> KEEFER, Larry, K.; 7016 River Road, Bethesda, MD 20817 (US). HUTSELL, Thomas, C.; 26 Farm Spring Lane, North Oaks, MN 55127 (US). <b>(74) Agents:</b> GAGALA, Bruce, M. et al.; Leydig, Voit & Mayer, Ltd., Suite 4900, Two Prudential Plaza, Chicago, IL 60601-6780 (US).		<b>(81) Designated States:</b> AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> USE OF NITRIC OXIDE-RELEASING POLYMERS TO TREAT RESTENOSIS AND RELATED DISORDERS  <b>(57) Abstract</b>  Methods of amelioration, treatment and prevention for restenosis and related disorders are provided. Methods involve the administration of nitric oxide by a nitric oxide delivery means comprising a restenosis-ameliorating or therapeutically/prophylactically effective amount of a polymer to which is bound a nitric oxide-releasing N <sub>2</sub> O <sub>2</sub> <sup>-</sup> functional group or a compound comprising a nitric oxide-releasing N <sub>2</sub> O <sub>2</sub> <sup>-</sup> functional group. Also provided are nitric oxide delivery means comprising such nitric oxide-releasing polymers or compounds for use in such methods. Preferably, the delivery means is coated with a nitric oxide-releasing polymer, which may be biodegradable, and enables the controllable and predictable release of NO to a given site in such a manner that effective ameliorating, prophylactic or therapeutic dosing is realized.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

## USE OF NITRIC OXIDE-RELEASING POLYMERS TO TREAT RESTENOSIS AND RELATED DISORDERS

This application is a continuation-in-part of U.S. patent application serial no. 08/121,169, filed September 14, 1993, which, in turn, is a continuation-in-part of U.S. application serial no. 07/935,565, filed August 24, 1992. The entire disclosures of the '169 and '565 applications are incorporated herein by reference.

### Technical Field of the Invention

The present invention relates to a method of using nitric oxide-releasing agents and polymers to treat, ameliorate or prevent the onset of restenosis and related disorders. The present invention also relates to nitric oxide delivery means comprising nitric oxide-releasing agents or polymers for use in the method.

15

### Background of the Invention

Over half a million interventional intravascular procedures are performed each year. While such invasive procedures continue to improve over time, as many as 30-50% of the procedures performed each year fail as a result of restenosis. The reduction of restenosis is, therefore, often cited as the most critical factor in increasing the success realized in the treatment of cardiovascular disease through the use of interventional intravascular procedures, such as angioplasty, atherectomy, and procedures utilizing stents and laser technology.

In balloon angioplasty, for example, a small incision is made to an artery in the patient's leg or arm and a long hollow tube, called a guide catheter, is inserted into the artery. A thick guide wire and deflated balloon catheter are then inserted into the guide catheter and are carefully advanced through the patient's blood vessels using x-ray visualization. The deflated balloon is advanced until it reaches the site of

the luminal narrowing, at which point the physician inflates the balloon one or more times to a pressure of about 4-6 atm for about 60 sec. When inflated, the balloon cracks and fractures the plaque and stretches the muscle fiber in the artery wall beyond its ability to recoil completely. Although no plaque is removed in this procedure, the fracturing of the plaque and the stretching of the arterial wall increase the vessel lumen, thereby allowing for increased blood flow through the lumen.

The restenosis that accompanies such procedures is characterized by platelet aggregation and adhesion, smooth muscle cell proliferation, narrowing of the vessel lumen, restricted vasodilation, and an increase in blood pressure. Smooth muscle cells in the intimal layer of the artery have been reported to enter the growth cycle within about 2-3 days of these procedures and to proliferate for several days thereafter (intimal hyperplasia), the vast majority of smooth muscle cell proliferation reportedly being completed within 7 days (Stemerman, Am. J. Pathol., 73, 7-18 (1973)). Attempts have been made to provide nitric oxide as a means of treating platelet aggregation and the like.

Nitric oxide in its pure form, however, is a highly reactive gas having limited solubility in aqueous media (WHO Task Group on Environmental Health Criteria for Oxides of Nitrogen, Oxides of Nitrogen, Environmental Health Criteria 4 (World Health Organization: Geneva, 1977)). Nitric oxide, therefore, is difficult to introduce reliably into most biological systems without premature decomposition.

A number of compounds have been developed which are capable of delivering nitric oxide, including compounds which release nitric oxide upon being metabolized and compounds which release nitric oxide spontaneously in aqueous solution.

Those compounds which release nitric oxide upon being metabolized include the widely used nitrovasodilators glyceryl trinitrate and sodium nitroprusside (Ignarro et al., J. Pharmacol. Exp. Ther., 218, 739-749 (1981); Ignarro, Annu. Rev. Pharmacol. Toxicol., 30, 535-560 (1990); Kruszyna et al., Toxicol. Appl. Pharmacol., 91, 429-438 (1987); Wilcox et al., Chem. Res. Toxicol., 3, 71-76 (1990)), which are relatively stable but release nitric oxide on activation. While this feature may be an advantage in some applications, it also can be a significant liability. For example, tolerance to glyceryl trinitrate can develop via the exhaustion of the relevant enzyme/cofactor system (Ignarro et al., Annu. Rev. Pharmacol. Toxicol., 25, 171-191 (1985); Kuhn et al., J. Cardiovasc. Pharmacol., 14 (Suppl. 11), S47-S54 (1989)). Also, prolonged administration of nitroprusside results in the metabolic production of cyanide, which leads to toxicity (Smith et al., "A Potpourri of Biologically Reactive Intermediates" in Biological Reactive Intermediates IV. Molecular and Cellular Effects and Their Impact on Human Health (Witmer et al., eds.), Advances in Experimental Medicine and Biology Volume 283 (Plenum Press: New York, 1991), pp. 365-369). S-Nitroso-N-acetylpenicillamine has been reported to release nitric oxide in solution and to be effective at inhibiting DNA synthesis (Garg et al., Biochem. and Biophys. Res. Comm., 171, 474-479 (1990)).

Numerous nitric oxide-nucleophile complexes have been described, e.g., Drago, ACS Adv. Chem. Ser., 36, 143-149 (1962). See also Longhi and Drago, Inorg. Chem., 2, 85 (1963). Some of these complexes are known to evolve nitric oxide on heating or hydrolysis, e.g., Maragos et al., J. Med. Chem., 34, 3242-3247 (1991).

A very important class of such agents is the just-named nitric oxide-nucleophile complexes (NONOates). Recently, a method for treating cardiovascular disorders in a mammal with certain nitric oxide-nucleophile

complexes was disclosed, e.g. in U.S. Patent No. 4,954,526. These compounds contain the anionic  $N_2O_2^-$  group or derivatives thereof. See also, Maragos et al., supra. Many of these compounds have proven especially promising pharmacologically because, unlike nitrovasodilators such as nitroprusside and nitroglycerin, they release nitric oxide without first having to be activated. The only other series of drugs currently known to be capable of releasing nitric oxide purely spontaneously is the S-nitrosothiol series, compounds of structure R-S-NO (Stamler et al., Proc. Natl. Acad. Sci. U.S.A., 89, 444-448 (1992)); however, the R-S-NO $\rightarrow$ NO reaction is kinetically complicated and difficult to control (Morley et al., J. Cardiovasc. Pharmacol., 21, 670-676 (1993)). Similarly, compounds like molsidomine and linsidomine not only require activation to release NO, but they also release undesirable free radicals. The NONOates, therefore, are thus unique among currently known drugs in that they decompose at any given pH by a first-order reaction to provide doses of nitric oxide that can be predicted, quantified, and controlled. See, e.g., Maragos et al., supra.

Nitric oxide/nucleophile complexes which release nitric oxide in aqueous solution are also disclosed in U.S. Patent Nos. 5,039,705, 5,155,137, 5,185,376, 5,208,233, 5,212,204, 5,250,550, 5,366,977, and 5,389,675, as being useful cardiovascular agents (see also Maragos et al., J. Med. Chem., 34, 3242-3247 (1991)).

Despite the promise of the nitric oxide/nucleophile adducts that have been investigated, their pharmacological application has been limited by their tendency to distribute evenly throughout the medium. Such even distribution is a great advantage in many research applications, but tends to compromise their selectivity of action. Another limitation to the



application of these nitric oxide/nucleophile adducts is their propensity for relatively rapid release of nitric oxide, which may necessitate frequent dosing to achieve a prolonged biological effect. The nitric oxide-releasing polymers of the present invention overcome these limitations by enabling concentrated and localized release of NO at a given site in a controllable and predictable manner such that effective dosing may be realized.

There remains a need, however, for an effective method of preventing, ameliorating and treating restenosis. Accordingly, the present invention provides a method of prevention, amelioration and treatment for restenosis and related disorders which overcomes the disadvantages of currently available treatment methods, and delivery means for use in the prevention, amelioration and treatment of restenosis and related disorders. These and other objects and advantages of the present invention, as well as additional inventive features, will be apparent from the description of the invention provided herein.

#### Summary of the Invention

The present invention provides methods of preventing, alleviating, ameliorating and treating restenosis and related disorders comprising the administration of a delivery means comprising a nitric oxide-releasing agent, such as a compound comprising a nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group or a polymer to which is bound a nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group, in an amount sufficient to release a restenosis-ameliorating or prophylactically or therapeutically effective amount of nitric oxide. The method of treatment involves the administration of the delivery means comprising a nitric oxide-releasing agent after the onset of signs of restenosis or a related disorder, whereas the method of prevention involves the

administration of the delivery means comprising a nitric oxide-releasing agent prior to the onset of signs of restenosis or a related disorder. Preferably, the delivery means is coated with or made of a nitric oxide-releasing polymer and enables the controllable and predictable localized release of NO to a given site in such a manner that effective restenosis-ameliorating or prophylactic or therapeutic dosing is realized. The delivery means may be biodegradable. Delivery means comprising the nitric oxide-releasing agent are also provided.

#### Brief Description of the Drawings

Figure 1 is the chemiluminescence detector response to nitric oxide generated from the polymer-bound nitric oxide-releasing  $N_2O_2^-$  functional group composition of Example 3 in accordance with the invention.

Fig. 2 is a graph illustrating the time course of vascular relaxation with different doses of the polymer-bound nitric oxide-releasing composition of Example 1.

Fig. 3 is a graph illustrating the time course of vascular relaxation with different doses of the polymer-bound nitric oxide-releasing composition of Example 2.

Figure 4A is a graph of % [ $^3H$ ]thymidine incorporation versus concentration ( $\mu M$ ) for A375 human melanoma cells (A375 cells) treated with  $(H_2NCH_2CH_2)_2NH$  (DETA) and DETA $\cdot$ 2NO (DETA/NO).

Figure 4B is a graph of % [ $^3H$ ]thymidine incorporation versus concentration ( $\mu M$ ) for rat aorta smooth muscle cells (RA-SM cells) treated with DETA and DETA/NO.

Figure 5A is a graph of cell number ( $\times 10^{-3}$ ) versus time (days) for RA-SM cells not treated or treated over a seven-day period with DETA/NO on day 1, days 1 and 3, or days 1, 3, and 5.

Figure 5B is a graph of cell number ( $\times 10^{-3}$ ) versus time (days) for RA-SM cells not treated or treated over a



seven-day period with DETA on day 1, days 1 and 3, or days 1, 3, and 5.

Figure 6 is a bar graph of % change in platelet aggregation in rabbits versus time post-injection (1 min or 30 min) with Et<sub>2</sub>N[N(O)NO]Na (DEA/NO), spermine•2NO (SPER/NO), sodium nitroprusside (NaNp), or aspirin (ASA).

Figure 7 is a graph of mean arterial pressure (MAP) in rabbits versus time (min) after intravenous injection with DEA/NO, SPER/NO, or NaNp.

Figure 8 is a graph of platelets deposited (x 10<sup>-9</sup>) at a thrombogenic site (Dacron graft) in an A-V shunt in baboons versus time of exposure (min) to



(MAHMA/NO).

## Detailed Description of the Invention

The present invention provides methods for the prophylactic, ameliorating and therapeutic treatment of restenosis and related disorders in a mammal.

Alleviation of the restenosis may also be achieved. The prophylactic method involves the administration to a mammal, in particular a human, of nitric oxide by a nitric oxide delivery means comprising a prophylactically effective amount of a nitric oxide-releasing agent, such as a compound comprising a nitric oxide-releasing N<sub>2</sub>O<sub>2</sub><sup>-</sup> functional group or a polymer to which is bound a nitric oxide-releasing N<sub>2</sub>O<sub>2</sub><sup>-</sup> functional group capable of locally releasing nitric oxide to a site at risk for restenosis or a related disorder in the mammal. The ameliorating or therapeutic method involves the administration of nitric oxide by a nitric oxide delivery means comprising a therapeutically effective amount of the nitric oxide-releasing agent to a site already affected by restenosis or a related disorder in the mammal. Related disorders refers to conditions wherein the vasculature is affected

by one or more of the following: platelet aggregation, platelet adhesion, smooth muscle cell proliferation, vasoconstriction, and/or increased blood pressure, whether the result of physical or chemical injury or disease. Localized release means release at or near the site at risk for or affected by restenosis or related disorder, irrespective of the actual route of administration employed. Nitric oxide delivery means encompasses the many forms in which the nitric oxide-releasing agent may be administered, such as vascular graft prosthetic implant, stent, heart valve, suture, drug pump, catheter, self-adhering means, liposome, microparticle, microsphere, bead, and disk as described more fully below.

Restenosis-ameliorating and prophylactically and therapeutically effective amounts are as described below with respect to dosages. Whether or not a particular mammal is at risk for restenosis or a related disorder may be determined by methods well-known to those of ordinary skill in the art. Factors such as gender, previous medical history, e.g., diabetes mellitus, smoking, unstable or variant angina pectoris, hypercholesterolemia and previous myocardial infarct, would be expected to place an individual at higher risk. Similarly, whether or not a particular mammal is affected by restenosis or a related disorder may be determined by methods known in the art, such as coronary angiography. The characterization of the restenosis may include the determination of the number and type of vessel(s) affected, portion of vessel affected, i.e., proximal or distal, and the complexity of the stenosis, e.g., length, degree of occlusion, eccentricity of lesion, ostial lesions, and degree of calcification. The present invention also provides various nitric oxide delivery means for use in the present prophylactic, restenosis-ameliorating and therapeutic methods as described more fully below.

The present invention is predicated on the discovery that useful pharmacological agents can be provided by incorporating nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional groups into a polymeric matrix. Accordingly, the  $\text{N}_2\text{O}_2^-$  functional group is "bound to the polymer" as that term has been defined herein. It has been discovered that incorporation of the  $\text{N}_2\text{O}_2^-$  functional group into a polymeric matrix provides a polymer-bound nitric oxide/nucleophile adduct composition that can be administered for localized release of NO to a biological site of interest. Site-specific delivery of the polymer-bound adduct composition enhances the selectivity of action of the nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group. If  $\text{N}_2\text{O}_2^-$  functional groups attached to the polymer are necessarily localized, then the effect of their nitric oxide release will be concentrated in the tissues with which they are in contact. If the polymer is soluble, selectivity of action can still be arranged, for example, by attachment to or derivatization of an antibody specific to the target tissue, such as an antibody to fibrin or tissue thromboplastin. Similarly, attachment of  $\text{N}_2\text{O}_2^-$  groups to small peptides that mimic the recognition sequences of ligands for important receptors provides localized concentrated effect of nitric oxide release, as would attachment to oligonucleotides capable of site-specific interactions with target sequences in a nucleic acid.

Additionally; incorporation of the  $\text{N}_2\text{O}_2^-$  functional group into a polymeric matrix can reduce the propensity of the nitric oxide/nucleophile adduct for the relatively rapid release of nitric oxide. This prolongs the release of nitric oxide by the  $\text{N}_2\text{O}_2^-$  functional group, and allows for efficient dosing to achieve a desired biological effect so the frequency of dosing can be reduced.

While not being bound to any particular theory, it is believed that longevity of nitric oxide release in the polymer-bound nitric oxide/nucleophile adduct

compositions of the present invention is to be attributed both to the physical structure of the composition and to electrostatic effects. Thus, it is believed that if the polymer is an insoluble solid,  $\text{N}_2\text{O}_2^-$  groups near the surface of the particle should be available for rapid release while those that are more deeply imbedded are sterically shielded, requiring more time and/or energy for the nitric oxide to work its way into the medium. Unexpectedly, it has been found that increasing positive charge in the vicinity of an  $\text{N}_2\text{O}_2^-$  functional group also tends to increase the half-life of nitric oxide generation. The mechanism of this rate retardation may be attributable simply to repulsive electrostatic interactions, i.e., increasing the number of  $\text{H}^+$ -repelling positive charges in the vicinity of the  $\text{N}_2\text{O}_2^-$  groups inhibits attack of positively charged  $\text{H}^+$  ions on the  $\text{N}_2\text{O}_2^-$  functional group and slows the rate of its  $\text{H}^+$ -catalyzed decomposition (Hrabie et al., J. Org. Chem., 58, 1472-1476 (1993)).


The nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional groups that are bound to the polymer generally are capable of releasing nitric oxide in an aqueous environment spontaneously upon contacting an aqueous environment, i.e., they do not require activation through a redox reaction or electron transfer such as is required for glyceryl trinitrate and sodium nitroprusside. Some of the nitric oxide/nucleophile complexes useful in the context of the present invention do require activation by particular means, but only as necessary to free the nitric oxide releasing  $\text{X}[\text{N}(\text{O})\text{NO}]^-$  group in the vicinity of the particular cells of interest. As an example, covalent attachment of a protecting group to the anionic  $[\text{N}(\text{O})\text{NO}]^-$  function provides a means of postponing nitric oxide release until the molecule reaches an organ capable of metabolically removing the protecting group. By choosing a protecting group that is selectively cleaved by enzymes specific to a tumor, biological disorder,

cell, or tissue of interest, for example, the action of the nitric oxide/nucleophile complex can be targeted to maximize the desired effect. While the polymer-bound nitric oxide releasing compositions of the present invention are capable of releasing nitric oxide in an aqueous solution, such a polymer preferably releases nitric oxide under physiological conditions.


The nitric oxide releasing  $N_2O_2^-$  functional group is preferably a nitric oxide/nucleophile adduct, i.e., a complex of nitric oxide and a nucleophile, most preferably a nitric oxide/nucleophile complex which contains the anionic moiety  $X[N(O)NO]^-$ , where X is any suitable nucleophile residue. The nucleophile residue is preferably that of a primary amine (e.g.,  $X = (CH_3)_2CHNH$ , as in  $(CH_3)_2CHNH[N(O)NO]Na$ ), a secondary amine (e.g.,  $X = (CH_3CH_2)_2N$ , as in  $(CH_3CH_2)_2N[N(O)NO]Na$ ), a polyamine (e.g.,  $X = \text{spermine}$ , as in the zwitterion  $H_2N(CH_2)_3NH_2^+(CH_2)_4N[N(O)NO]^- (CH_2)_3NH_2$ ,  $X = \text{(ethylamino)ethylamine}$ , as in the zwitterion  $CH_3CH_2N[N(O)NO]^-CH_2CH_2NH_3^+$ , or  $X = 3\text{-(n-propylamino)propylamine}$ , as in the zwitterion  $CH_3CH_2CH_2N[N(O)NO]^-CH_2CH_2CH_2NH_3^+$ ), or oxide (i.e.,  $X = O^-$ , as in  $NaO[N(O)NO]Na$ ), or a derivative thereof. Such nitric oxide/nucleophile complexes are stable solids and are capable of delivering nitric oxide in a biologically usable form at a predictable rate.

The nucleophile residue is preferably not an entity such as that of sulfite (e.g.,  $X = SO_3^-$ , as in  $NH_4O_3S[N(O)NO]NH_4$ ) even though the complex is a stable compound, since it is capable of releasing nitric oxide in an aqueous environment only under harsh, nonphysiological conditions.


Other suitable nitric oxide/nucleophile complexes include those having the following formulas:





wherein J is an organic or inorganic moiety, including, for example, a moiety which is not linked to the nitrogen of the  $\text{N}_2\text{O}_2^-$  group through a carbon atom,  $\text{M}^{+x}$  is a pharmaceutically acceptable cation, where x is the valence of the cation, a is 1 or 2, and b and c are the smallest integers that result in a neutral compound, preferably such that the compound is not a salt of alanosine or dopastin, as described in U.S. Patent No. 5,212,204, incorporated herein by reference;



wherein b and d are the same or different and may be zero or one,  $\text{R}_1$ ,  $\text{R}_2$ ,  $\text{R}_3$ ,  $\text{R}_4$ , and  $\text{R}_5$  are the same or different and may be hydrogen,  $\text{C}_{3-8}$  cycloalkyl,  $\text{C}_{1-12}$  straight or branched chain alkyl, benzyl, benzoyl, phthaloyl, acetyl, trifluoroacetyl, p-toluyyl, t-butoxycarbonyl, or 2,2,2-trichloro-t-butoxycarbonyl, and x, y, and z are the same or different and are integers from 2 to 12, as described in U.S. Patent No. 5,155,137, incorporated herein by reference;




wherein B is  or 

40  $\text{R}_6$  and  $\text{R}_7$  are the same or different and may be hydrogen,  $\text{C}_{3-8}$  cycloalkyl,  $\text{C}_{1-12}$  straight or branched chain alkyl,




benzyl, benzoyl, phthaloyl, acetyl, trifluoroacetyl, p-toluyyl, t-butoxycarbonyl, or 2,2,2-trichloro-t-butoxycarbonyl, f is an integer from 0 to 12, with the proviso that when B is the substituted piperazine moiety

5



then f is an integer from 2 to 12, as described in U.S. Patent 5,250,550 incorporated herein by reference;


10



15

wherein  $\text{R}_8$  is hydrogen,  $\text{C}_{3-8}$  cycloalkyl,  $\text{C}_{1-12}$  straight or branched chain alkyl, benzyl, benzoyl, phthaloyl, acetyl, trifluoroacetyl, p-toluyyl, t-butoxycarbonyl, or 2,2,2-tri-chloro-t-butoxycarbonyl,  $\text{R}_9$  is hydrogen or a  $\text{C}_1\text{--C}_{12}$  straight or branched chain alkyl, and g is 2 to 6, as described in U.S. Patent No. 5,250,550, incorporated herein by reference;

25



30


wherein  $\text{R}_1$  and  $\text{R}_2$  are independently selected from the group consisting of a straight chain or branched chain  $\text{C}_1\text{--C}_{12}$  alkyl group and a benzyl group, preferably such that no branch occurs on the alpha carbon atom, or else  $\text{R}_1$  and  $\text{R}_2$ , together with the nitrogen atom, are bonded to form a heterocyclic group, preferably a pyrrolidino, piperidino, piperazino or morpholino group,  $\text{M}^{+\text{x}}$  is a pharmaceutically acceptable cation, and x is the valence of the cation, as described in U.S. Patent Nos. 5,039,705

40

and 5,208,233 and U.S. patent application Serial No. 08/017,270, filed February 12, 1993, and incorporated herein by reference;



wherein M is a pharmaceutically acceptable metal, or, where x is at least two, a mixture of two different  
 10 pharmaceutically acceptable metals, L is a ligand different from  $(R^1R^2N-N_2O_2)$  and is bound to at least one metal,  $R^1$  and  $R^2$  are each organic moieties and may be the same or different (preferably where M is copper, x is one, L is methanol, and y is one, that at least one of  $R^1$   
 15 or  $R^2$  is not ethyl), x is an integer of from 1 to 10,  $x'$  is the formal oxidation state of the metal M, and is an integer of from 1 to 6, y is an integer of from 1 to 18, and where y is at least 2, the ligands L may be the same or different, z is an integer of from 1 to 20, and K is a  
 20 pharmaceutically acceptable counterion to render the compound neutral to the extent necessary, as described in U.S. patent application Serial No. 07/858,885, filed March 27, 1992 and incorporated herein by reference;



wherein R is  $C_{2-8}$  lower alkyl, phenyl, benzyl, or  $C_{3-8}$  cycloalkyl, any of which R groups may be substituted by  
 30 one to three substituents, which are the same or different, selected from the group consisting of halo, hydroxy,  $C_{1-8}$  alkoxy,  $-NH_2$ ,  $-C(O)NH_2$ ,  $-CH(O)$ ,  $-C(O)OH$ , and  $-NO_2$ , X is a pharmaceutically acceptable cation, a pharmaceutically acceptable metal center, or a  
 35 pharmaceutically acceptable organic group selected from the group consisting of  $C_{1-8}$  lower alkyl,  $-C(O)CH_3$ , and  $-C(O)NH_2$ , and y is one to three, consistent with the valence of X, as described in U.S. Patent No. 4,954,526 and incorporated herein by reference; and



5 wherein  $R_1$  and  $R_2$  are independently chosen from  $C_{1-12}$  straight chain alkyl,  $C_{1-12}$  alkoxy or acyloxy substituted straight chain alkyl,  $C_{2-12}$  hydroxy or halo substituted straight chain alkyl,  $C_{3-12}$  branched chain alkyl,  $C_{3-12}$  hydroxy, halo, alkoxy, or acyloxy substituted branched chain alkyl,  $C_{3-12}$  straight chain olefinic and  $C_{3-12}$  branched chain olefinic which are unsubstituted or substituted with hydroxy, alkoxy, acyloxy, halo or benzyl, or  $R_1$  and  $R_2$ , together with the nitrogen atom to which they are bonded, form a heterocyclic group, preferably a pyrrolidino, piperidino, piperazino or morpholino group, and  $R_3$  is a group selected from  $C_{1-12}$  straight chain and  $C_{3-12}$  branched chain alkyl which are unsubstituted or substituted by hydroxy, halo, acyloxy or alkoxy,  $C_{2-12}$  straight chain or  $C_{3-12}$  branched chain olefinic which are unsubstituted or substituted by halo, alkoxy, acyloxy or hydroxy,  $C_{1-12}$  unsubstituted or substituted acyl, sulfonyl and carboxamido; or  $R_3$  is a group of the formula  $-(CH_2)_n-ON=N(O)NR_1R_2$ , wherein  $n$  is an integer of 2-8, and  $R_1$  and  $R_2$  are as defined above; preferably  $R_1$ ,  $R_2$  and  $R_3$  do not contain a halo or a hydroxy substituent  $\alpha$  to a heteroatom, as described in U.S. patent application Serial No. 07/950,637 filed September 23, 1992.

30 Any of a wide variety of polymers can be used in the context of the present invention. It is only necessary that the polymer selected is biologically acceptable. Illustrative of polymers suitable for use in the present invention are polyolefins, such as polystyrene, polypropylene, polyethylene, polytetrafluorethylene, polyvinylidene difluoride, and polyvinylchloride; polyethylenimine or derivatives thereof; polyethers, such as polyethyleneglycol; polyesters, such as poly(lactide/glycolide); polyamides, such as nylon;

polyurethanes; colestipol and derivatives thereof; biopolymers, such as peptides, proteins, oligonucleotides, nucleic acids, starburst dendrimers, and the like, and macromolecules, such as antibodies.

5       The physical and structural characteristics of the polymers suitable for use in the present invention are not narrowly critical, but rather will depend on the end use application. It will be appreciated by those skilled in the art that, where the polymer-bound nitric  
10 oxide/nucleophile adduct compositions of the present invention are intended for local or relatively short term administration, they need not be biodegradable. For some uses, such as post-angioplasty coronary bypass surgery or for intimal hyperplasia associated with vascular graft  
15 implants or the like, it may be desirable that the polymer of the polymer-bound compositions slowly dissolve in a physiological environment.

      The polymer-bound nitric oxide releasing agents may be administered in a wide variety of forms of delivery  
20 means. Any delivery means should adequately protect the integrity of the nitric oxide prior to its release and should control the release of the nitric oxide at such a rate, in such an amount, and in such a location as to serve as an effective means of preventing or treating  
25 restenosis. For example, delivery means for local administration or administration for localized release include, but are not limited to, sutures, vascular implants (e.g., endoluminal or periadventitial), stents, heart valves, drug pumps, drug-delivery catheters  
30 (pressure-driven, iontophoretic), self-adhering means (vessel coatings) such as endoluminal implants, liposomes, microparticles, microspheres, beads, disks or other devices. The advantages of local administration or release include the ability to attain effective  
35 concentrations of drug at the target site more quickly, the use of a smaller dose, and the realization of fewer toxic side effects than systemic administration and

release. Delivery means for systemic administration for localized release include, but are not limited to, solutions, suspensions, emulsions, capsules, sachets, tablets, dermal (topical) patches, lozenges, aerosols, liposomes, microparticles, microspheres, beads, prodrugs, such as a cholesterol avid prodrug, for release into a vascular lesion, tissue-specific antibodies, such as antibodies to fibrin or tissue thromboplastin, small peptides that mimic ligand recognition sequences, and sequence-specific oligonucleotides as described above. The polymer, itself, may be structurally sufficient to serve as a form of delivery means. Alternatively, the polymer-bound composition may be incorporated into or coated onto other matrices, substrates or the like, or it may be microencapsulated, or the like.

The nitric oxide-releasing complexes having  $\text{N}_2\text{O}_2^-$  functional groups, including the compounds described above, may be bound to the polymer support in a number of different ways. For example, the compounds described above may be bound to the polymer by coprecipitation of such compounds with the polymer. Coprecipitation involves, for example, solubilizing both the polymer and the nitric oxide/nucleophile compound and evaporating the solvent. Monomers containing the  $\text{N}_2\text{O}_2^-$  group also may be dissolved in molten polymer which, upon solidification when the temperature is lowered, contains a rather uniform distribution of  $\text{N}_2\text{O}_2^-$  groups within the matrix.

Alternatively, nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional groups may be bound to the polymer by formation of a nitric oxide/nucleophile complex of the types and having the formulas of those described above; in situ on the polymer. The  $\text{N}_2\text{O}_2^-$  functional group may be attached to an atom in the backbone of the polymer, or it may be attached to a group pendant to the polymer backbone, or it may simply be entrapped in the polymer matrix. Where the  $\text{N}_2\text{O}_2^-$  functional group is in the polymer backbone, the polymer includes in its backbone



sites which are capable of reacting with nitric oxide to bind the nitric oxide for future release. For example, where the polymer is polyethylenimine, the polymer includes nucleophilic nitrogen atoms which react with nitric oxide to form the  $N_2O_2^-$  functional group at the nitrogen in the backbone. Where the  $N_2O_2^-$  functional group is a group pendant to the polymer backbone, the polymer contains, or is derivatized with, a suitable nucleophilic residue capable of reacting with nitric oxide to form the  $N_2O_2^-$  functionality. Reaction of the polymer which contains a suitable nucleophilic residue, or of the suitably derivatized polymer, with nitric oxide thus provides a polymer-bound nitric oxide-releasing  $N_2O_2^-$  functional group. To form the polymer-bound nitric oxide-releasing  $N_2O_2^-$  functional group, a net positive charge is imparted to the polymer near the site on the polymer where the  $N_2O_2^-$  functional group is formed.

One skilled in the art will appreciate that suitable methods of administering the nitric oxide-releasing agents of the present invention to an animal are available, and, although more than one route can be used to administer a particular composition, a particular route can provide a more immediate and more effective reaction than another route. Pharmaceutically acceptable carriers are also well-known to those who are skilled in the art. The choice of carrier will be determined in part by the particular composition, as well as by the particular method used to administer the composition. Accordingly, there is a wide variety of suitable formulations of the pharmaceutical composition of the present invention.

Formulations suitable for oral administration can consist of (a) liquid solutions, such as an effective amount of the polymer-bound composition dissolved in diluents, such as water or saline, (b) capsules, sachets or tablets, each containing a predetermined amount of the active ingredient, as solids or granules, (c) suspensions



in an appropriate liquid, and (d) suitable emulsions. Tablet forms can include one or more of lactose, mannitol, corn starch, potato starch, microcrystalline cellulose, acacia, gelatin, colloidal silicon dioxide, croscarmellose sodium, talc, magnesium stearate, stearic acid, and other excipients, colorants, diluents, buffering agents, moistening agents, preservatives, flavoring agents, and pharmacologically compatible carriers. Lozenge forms can comprise the active ingredient in a flavor, usually sucrose and acacia or tragacanth, as well as pastilles comprising the active ingredient in an inert base, such as gelatin and glycerin or sucrose and acacia emulsions, gels, and the like containing, in addition to the active ingredient, such carriers as are known in the art.

The biodegradable nitric oxide-releasing agents of the present invention, alone or in combination with other suitable components, can be made into aerosol formulations to be administered via inhalation. These aerosol formulations can be placed into pressurized acceptable propellants, such as dichlorodifluoromethane, propane, nitrogen, and the like.

Formulations suitable for parenteral administration include aqueous and non-aqueous, isotonic sterile injection solutions, which can contain anti-oxidants, buffers, bacteriostats, and solutes that render the formulation isotonic with the blood of the intended recipient, and aqueous and non-aqueous sterile suspensions that can include suspending agents, solubilizers, thickening agents, stabilizers, and preservatives. The formulations can be presented in unit-dose or multi-dose sealed containers, such as ampules and vials, and can be stored in a freeze-dried (lyophilized) condition requiring only the addition of the sterile liquid carrier, for example, water, for injections, immediately prior to use. Extemporaneous injection solutions and suspensions can be prepared from

sterile powders, granules, and tablets of the kind previously described.

The dose administered to an animal, particularly a human, in the context of the present invention should be sufficient to effect a restenosis-ameliorating or prophylactic or therapeutic response in the animal over a reasonable time frame. The dose will be determined by the strength of the particular nitric oxide-releasing agent employed, the type of delivery means employed, the route of administration, the condition and weight of the animal to be treated, the timing of administration, i.e., prior to the onset of restenosis or related disorder or after the onset of restenosis or related disorder, and the length of time of administration. The size of the dose also will be determined by the existence, nature, and extent of any adverse side-effects that might accompany the administration of a particular composition. A suitable dose, for example, is about 0.05 mg-100 mg of nitric oxide. The dose may be administered acutely or chronically as dictated by the condition being treated, ameliorated or prevented.

The following examples further illustrate the present invention, but do not limit the scope thereof.

In the Examples, chemiluminescence analysis for total recoverable nitric oxide from polymers containing the nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group by acid treatment was carried out as follows:

The analysis of NO adducts, i.e., polymers containing the nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group, was done on a nitric oxide analyzer and was patterned after the procedure of Maragos et al., J. Med. Chem., 34, 3242-3247 (1991). A reactor vessel fitted with a septum was charged with a small aliquot of the polymer to be studied and the system was purged with helium for several minutes to remove traces of oxygen. Two milliliters of 10 mM sulfuric acid was added by injection through the septum to begin reaction. Gaseous

effluent was swept continuously via a fritted glass bubbler positioned at the bottom of the reactor vessel (i.e., immersed in the acid solution) into a chemiluminescence detector (Thermal Energy Analyzer Model 502LC, Thermedics, Inc., Woburn, MA). The area of the resulting chemiluminescence signal versus time curve was electronically computed and compared with that of a known quantity of nitric oxide gas standard to determine the amount of nitric oxide produced by acid treatment of the polymer aliquot.

This procedure was used to estimate the total amount of nitric oxide recoverable from the polymer. To estimate the rate of nitric oxide generation under physiological conditions, the inventive polymers were subjected to a procedure identical to that described above, except that 2 ml of 10 mM phosphate buffer, pH 7.4, was injected into the reactor vessel in place of the sulfuric acid solution to start the reaction.

20

## EXAMPLES

### Example 1

This example illustrates the preparation of a polymer-bound nitric oxide/nucleophile complex by coprecipitation of a monomeric form thereof with a polymer.

One gram of polymer [poly(lactide/glycolide, 50:50) from MediSorb] was dissolved in 2 ml of tetrahydrofuran. To the solution was added 300 mg of DETA/NO,  $[H_2N(CH_2)_2]_2N-N_2O_2H$ , zwitterionic form, and the mixture was stirred under an argon stream to remove solvent slowly until the mixture became too viscous to stir. The mixture was then placed in a vacuum oven (ca. 1 mm) at 30°C for 5 hours to remove the residual solvent. The mixture was finally pressed on a carver press at 20,000 lbs. at 140°F for 5 minutes. A 1" x 1" film, 44 mils thick, was thus prepared. Using the chemiluminescence procedure described above, nitric oxide was recovered

from this polymer on treatment with acid at the rate of 8 nmol of NO per milligram of solid.

#### Example 2

5        This example illustrates the preparation of a polymer-bound nitric oxide/nucleophile adduct in which the  $\text{N}_2\text{O}_2^-$  functional group is bound directly to an atom in the polymer backbone.

10        A slurry of 10.0 g of polyethylenimine on silica gel (Aldrich) in 150 ml of acetonitrile was stirred for 3 days under a nitric oxide pressure of 5 atm or 75-80 psig. The resulting orange solid was filtered, washed with acetonitrile and then ether, and dried in vacuo for 6 h. Using the chemiluminescence procedure described  
15        above, it was determined that nitric oxide was recovered from this polymer on treatment with acid at the rate of 3 nmol/mg.

Control experiments with polymer that had not been exposed to NO produced no chemiluminescence signal.

20

#### Example 3

25        This example illustrates the preparation of a polymer containing nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  groups that are attached to nucleophile residues pendant on the polymer backbone by the reaction of a primary amine with a derivatized polystyrene.

30        An aminostyrene polymer was prepared by warming 3.0 g of chloromethylated polystyrene (1% divinylbenzene; 1.09 mEq Cl per gram; 200-400 mesh; Polysciences, Inc., Warrington, PA) in 20 ml of n-propyl-1,3-propanediamine to 60°C in an oil bath and swirling periodically for 5 days. The polymer was then filtered, washed repeatedly with water, then methanol and finally dichloromethane, and dried in vacuo for 24 h. Elemental analysis showed  
35        this material to be 2.21% nitrogen, indicating that approximately 80% of the chlorines had been replaced by propylpropanediamino groups.

A slurry of 1.0 g of the aminopolystyrene polymer in 50 ml of acetonitrile was placed under 5 atm of nitric oxide in a Parr apparatus and shaken intermittently for 3 days. The product was filtered and dried in vacuo to  
5 yield 0.84 g of cream colored polymer. The elemental analysis (C: 87.32; H: 8.00; N: 2.45) revealed that approximately one-third of the amino side chains became attached to  $\text{N}_2\text{O}_2^-$  groups under these conditions.

Using the chemiluminescence procedure described  
10 above, it was demonstrated that nitric oxide can be recovered from  $\text{N}_2\text{O}_2^-$  group-containing polymer prepared as described above. The observed chemiluminescence detector response as a function of time and the amount of nitric oxide regenerated when the polymer was treated with acid  
15 are illustrated in Figure 1. As can be seen, only small amounts of nitric oxide were evolved from the solid, itself, but when 2 ml of 10 mM sulfuric acid was injected via a septum, a sudden pulse of nitric oxide appeared. Integration of this apparently first-order generation of  
20 nitric oxide over time indicated that 11 nmol of nitric oxide was recovered from 1 mg of polymer.

The reaction was repeated using 10 mM phosphate buffer at pH 7.4 in place of the sulfuric acid to verify the slow release of nitric oxide at physiological pH.  
25 The chemiluminescence detector showed that nitric oxide was generated from this polymer much more slowly.

#### Example 4

This example illustrates the preparation of a  
30 polyethylene glycol-based NO-releasing polymer using two different methods of preparation.

In one method, 20 mg of 1,1-diethyl-2-hydroxy-2-nitrosohydrazine sodium salt (DEA/NO) and 2.5 g of polyethyleneglycol-1450 (Union Carbide) were dissolved in  
35 25 ml of methanol. The homogenous solution was placed on a rotary evaporator at 40°C and the solvent was removed under vacuum to give a uniform solid solution. The



sample was stored in a clear glass vial, under ordinary laboratory lighting, at ambient temperature and atmosphere. The stability of the formulation was followed over a period of seven days. The measurements were carried out by monitoring the absorbance of the polymer at the 250 nm peak in the electronic spectrum. No changes in the absorbance were observed in this time period.

In a second method, 2.5 g of polyethylene glycol-1450 was heated to 46°C until completely melted. To the liquid polyethylene glycol was added 36 mg (0.232 mmol) of DEA/NO and the container was placed on a vortex mixer. A homogeneous solution was attained that gradually solidified upon cooling to ambient temperature. The stability of the solution was monitored as described above. No change in the absorbance for the 250 nm chromophore was observed at seven weeks of storage.

#### Example 5

This example illustrates the preparation of a polymer composed of a polyamine/nitric oxide complex N-[4-[1-(3-aminopropyl)-2-hydroxy-2-nitrosohydrazino)butyl]-1,3-propanediamine, zwitterionic form (SPER/NO); and polyethylene glycol.

A 1.2% (w/w) solution of KOH in polyethylene glycol-1450 (Union Carbide) was prepared in aqueous medium, and evaporated to dryness under vacuum (PEG-KOH). To 1.144 g of molten PEG-KOH was added 11.65 mg (0.042 mmol) of SPER/NO and the resulting mixture was blended to a uniform mass. No decrease was observed in the absorbance after five weeks of storage at room temperature in a clear glass vial.

#### PHARMACOLOGY EXPERIMENT

In the test procedures utilized, thoracic aortic rings from New Zealand White rabbits were suspended in pH 7.4 buffer at 37°C and a 10 g preload was applied to



each. After equilibration for 2 hours, the rings were precontracted with norepinephrine. The percent relaxation caused by adding the polymer-bound compositions of the present invention to the organ baths at successively increasing concentrations was measured. See Maragos et al., J. Med. Chem., 34, 3243-3247 (1991).

A polymer film as described in Example 1 was cooled on dry ice and a small piece was sliced off. This was placed onto a piece of weighed filter paper, which was reweighed to determine the amount of material present. The paper was folded to entrap the polymer inside, grasped with a hemostat, and immersed in the 50-ml buffer bath containing the precontracted aortic ring. As illustrated in Fig. 2, a piece of polymer weighing approximately 0.4 mg induced 30% relaxation in the ring, while 2.1 mg induced 80% relaxation. The data demonstrate that there was a positive response by the organ to the polymer-bound composition of this invention and that the response tended to increase as the dose administered was increased. Thus, the polymer-bound nucleophile/nitric oxide composition has a potent, dose-responsive cardiovascular effect.

The above experiment was repeated with the granular polymer produced in Example 2. A similar effect was observed, though it was less potent because this polymer contained fewer NO-releasing  $N_2O_2^-$  groups per gram than the polymer of Example 1.

Fig. 3 illustrates the time course of vascular relaxation when different doses of the polymer-bound nitric oxide-releasing composition of Example 2 are first exposed to the aortic ring, causing relaxation, then withdrawn from the organ bath, allowing recontraction to occur, then reintroduced into the organ bath, causing the vessel to dilate again. In this experiment, a 16-mg sample of the polymer-bound nitric oxide-releasing composition of Example 2 was immersed into the buffer bath. After 15% relaxation had been achieved, the sample

was removed from the bath. Upon removal of the polymer-bound composition, the degree of relaxation fell to approximately 11% over about 5 min. The sample of the polymer-bound composition was then returned to the bath, and a doubling of the degree of relaxation to about 25% was observed.

This experiment illustrates that the pharmacological effects of the polymer-bound nitric oxide/nucleophile composition of the present invention can be modulated as desired by controlling the extent and duration of contact between the polymer and the cells or tissues of interest. This feature is particularly advantageous, for example, to localize the effects of nitric oxide release to a specific target organ or situs.

15

#### Example 6

This example describes the effect of DETA/NO on DNA synthesis in A375 cells.

Quiescent A375 human melanoma cells were treated with DETA/NO or DETA (20-500  $\mu$ M) in Dulbecco's Modified Eagle's Medium (DMEM) + 10% fetal calf serum (FCS) for 22 hrs. DETA/NO is a NONOate that releases nitric oxide with a 20-hr half-life at 37°C and pH 7.4. Cells were then pulse-labeled with 1 mCi [ $^3$ H]thymidine for two hrs. Radioactivity was precipitated with trichloroacetic acid (TCA), recovered, and counted in accordance with methods well-known in the art.

Figures 4A and 4B are graphs of % [ $^3$ H]thymidine incorporation versus concentration ( $\mu$ M) for A375 and RA-SM cells; respectively, treated with DETA (●) and DETA/NO (□). Tritiated thymidine incorporation is expressed as percent of control (DMEM + 10% FCS)  $\pm$  1 S.D., where n = 3.

As shown in Figures 4A and 4B, DETA did not inhibit DNA synthesis in either A375 and RA-SM cells. By contrast, DETA/NO did inhibit DNA synthesis in both A375 and RA-SM cells, with an IC<sub>50</sub> of about 50-100  $\mu$ M and 20-50

μM, respectively. These results demonstrate that monomers analogous to the nitric oxide/nucleophile adducts employed in the polymeric compositions used in the methods and nitric-oxide-delivery means of the present invention inhibit cellular DNA synthesis.

#### Example 7

This example describes the effect of DETA/NO on proliferation of rat aorta smooth muscle (RA-SM) cells.

RA-SM cells in DMEM + 10% FCS were seeded at a concentration of 40,000 cells/well in a 24-well culture plate and were allowed to attach to the plate overnight. Cells were then not treated or treated over a seven-day period with 500 μM DETA/NO or DETA on day 1, days 1 and 3, or days 1, 3, and 5. Cells were harvested using trypsin:EDTA on days 1, 3, 5, and 7 and counted using a hemocytometer.

Figures 5A and 5B are graphs of cell number ( $\times 10^{-3}$ ) versus time (days) for RA-SM cells not treated (○) or treated over a seven-day period with DETA/NO or DETA, respectively, on day 1 (●), days 1 and 3 (□), or days 1, 3, and 5 (■). Cell proliferation is expressed as cell number  $\pm 1$  S.D., where  $n = 3$ .

As shown in Figure 5A and 5B, DETA had no effect on RA-SM cell proliferation. By contrast, DETA/NO inhibited RA-SM cell proliferation. A single dose of DETA/NO on day 1 resulted in a cell number on day 7 that was only about half that of the untreated control cells. Exposure of cells to doses of DETA/NO on days 1 and 3 led to an order of magnitude difference in the growth curves of the treated and untreated cells. Exposure of cells to doses of DETA/NO on days 1, 3 and 5 resulted in virtually complete suppression of RA-SM cell proliferation. However, removal of DETA/NO resulted in renewed cell proliferation. Accordingly, these results indicate that the continued presence of the NONOate is required in order to maintain inhibition of smooth muscle cell

proliferation; thus, growth of the cells was not irreversibly inhibited, but resumed when the NO source was removed.

5

#### Example 8

This example describes the effects of DEA/NO, SPER/NO, NaNp, and ASA on platelet aggregation in rabbits.

10 Anesthetized rabbits were treated with 50 nmol/kg DEA/NO ( $\text{Et}_2\text{N}[\text{N}(\text{O})\text{NO}]\text{Na}$ ), NaNp or ASA, or 500 nmol/kg SPER/NO, or 25 mg ASA, which is approximately 50,000 nmol/kg by intravenous bolus injection.

15 Figure 6 is a bar graph of % change in platelet aggregation in rabbits versus time post-injection (1 min or 30 min) with DEA/NO, SPER/NO, NaNp or ASA. Percent inhibition of platelet aggregation was determined by impedance aggregometry on whole blood withdrawn 1 min or 30 min after intravenous administration of a dose of a drug as indicated. Collagen was used as the aggregating agent. Values given are means  $\pm$  SEM, where  $n = 2-6$ . Values marked with an asterisk (\*) are significantly different ( $p < 0.05$ ) from those observed for untreated control blood.

20 As shown in Figure 6, 50 nmol/kg DEA/NO, 50 nmol/kg NaNp, 500 nmol/kg SPER/NO, and 25 mg ASA significantly inhibited platelet aggregation at 1 min post-injection, whereas only 500 nmol/kg SPER/NO and 25 mg ASA significantly inhibited platelet aggregation at 30 min post-injection. The magnitude and duration of the antiplatelet effects of DEA/NO and SPER/NO correlate with their spontaneous nitric oxide release rates in aqueous solution (Diodati et al., Thrombosis and Haemostasis, 70, 654-658 (1993)).

35

#### Example 9

This example describes the effects of DEA/NO, NaNp and SPER/NO on blood pressure in rabbits.

Anesthetized New Zealand white rabbits were treated with 50 nmol/kg DEA/NO, 500 nmol/kg SPER/NO or 50 nmol/kg NaNp by intravenous injection.

Figure 7 is a graph of mean arterial pressure (MAP) in rabbits versus time (min) after intravenous injection with 50 nmol/kg DEA/NO (•), 500 nmol/kg SPER/NO (▲), or 50 nmol/kg NaNp (O). Values given are means  $\pm$  S.D. MAP readings marked with an asterisk differ significantly ( $p < 0.05$ ) from pre-injection values.

As shown in Figure 7, 50 nmol/kg DEA/NO, 500 nmol/kg SPER/NO, and 50 nmol/kg NaNp all significantly reduced MAP within the first couple of minutes after administration. However, only 500 nmol/kg SPER/NO was effective in reducing MAP over the course of 30 min post-injection (Diodati et al., J. Cardiovasc. Pharmacol., 22, 287-292 (1993)). DEA/NO is a short-acting vasodilator, whereas SPER/NO is a longer-acting vasodilator, demonstrating significant hypotensive effects 30 min after injection.

20

#### Example 10

This example describes the effects of MAHMA/NO on platelet-dependent thrombosis in baboons.

An ex vivo arteriovenous shunt was established in baboons by cannulating the femoral artery and vein and connecting them with a length of tubing. The tubing was split in the middle and a drug infusion device was inserted. Downstream from the drug infusion device, a highly thrombogenic surface, e.g., a polyester graft, was inserted. Baboon blood platelets were made radioactive using  $^{111}\text{Indium}$ . Platelet accumulation on the polyester graft portion of the AV shunt was monitored for about one hour by measuring the increase in radioactivity with a gamma radiation counter. Increases in radioactivity indicate increases in platelet deposition on the polyester graft.



MAHMA/NO was infused through the porous wall of the drug infusion device so that it entered the blood stream in the slowest moving blood layers at the graft-blood interface, i.e., around the inside surface of the wall of the shunt. As the drug moved downstream, it reached concentrations along the vessel wall that are about 200 times those achieved by infusing drug uniformly into the blood flow field. Drugs which prevent thrombosis result in fewer platelets being deposited on the polyester graft.

Figure 8 is a graph of platelets deposited ( $\times 10^{-9}$ ) versus blood exposure (min) to MAHMA/NO. Figure 8 shows that, at high doses of MAHMA/NO, platelet deposition on the polyester graft was virtually eliminated. These results demonstrate that the localized administration of NONOates inhibits platelet adhesion and aggregation associated with thrombosis.

Given that 0.05 mg/hr of MAHMA/NO reduces platelet deposition at the graft by half, a graft coated with a nitric oxide-releasing polymer, for example, that releases NO at a rate of 0.5  $\mu\text{mol/hr}$  would be expected to similarly be useful to reduce platelet deposition.

#### Example 11

This example describes how a pharmaceutical composition comprising a NONOate may be prepared for intravenous or intraperitoneal injection and how it may be administered.

A stock solution of NO complex is prepared by weighing an appropriate amount of an NO complex into a volumetric flask. For example, for a  $10^{-2}$  M solution, 15.5 mg of DEA/NO is weighed into a 10 ml volumetric flask. Ice-cold 10 mM NaOH is added to bring the volume to 10 ml. From this stock solution, a dosing solution is prepared with an excess of phosphate-buffered saline (PBS), pH 7.4. For example, to prepare a  $10^{-6}$  M dosing solution, 10  $\mu\text{l}$  of  $10^{-2}$  M stock solution is diluted



1:10,000, i.e., to 10 ml with ice-cold PBS. This dosing solution is then used to provide a single dose or a continuous infusion to mammals, e.g., continuous infusion 1-2  $\mu\text{g/kg/min}$  for 5 minutes to lambs or a single daily intravenous injection of 10  $\mu\text{g/kg}$  to pigs.

#### Example 12

This example describes how a pharmaceutical composition comprising an NO adduct may be prepared for transdermal administration and how it may be administered.

An NO adduct is dissolved in enough ice-cold 10% distilled water in propylene glycol to provide the proper dosing concentration, e.g., 5  $\mu\text{mol}$ . 0.2 ml of the solution is applied to a shaved area of skin three times per week. Alternatively, the NO adduct is dissolved in ice-cold distilled water and then diluted 10-fold with cold propylene glycol and applied as before.

#### Example 13

This example describes how a balloon catheter comprising an NO adduct may be prepared and used to administer NO at the site of angioplasty.

An NO adduct is dissolved in water and maintained ice-cold. A balloon catheter is constructed from a microporous membrane, e.g., 150 Å polycarbonate membrane (Nucleopore®, Costar Corporation, Cambridge, MA or Fluoropore®, Millipore Corporation, Bedford, MA), and inserted into the blood vessel at the site of angioplasty. The NO adduct solution is used to inflate the balloon at the site of injury. An electrical current (e.g., 5 mA, 8-10 V) is passed through the balloon for 1-2 minutes. During this time, 100-300  $\mu\text{g}$  NO of adduct is expected to be transferred through the balloon into the vessel wall.

#### Example 14

This example describes how a biodegradable polymer comprising an NO adduct may be prepared and used to administer NO to an injured blood vessel.

In small increments with gentle stirring,  
5 polyoxypropylene-polyoxyethylene block co-polymer  
(Pluronic® F127 NF, BASF Corporation, Parsippany, NJ) is  
added to ice-cold water or phosphate-buffered saline, pH  
7.4, to make a 25% by weight solution. The appropriate  
amount of NO adduct to provide the needed dosage is  
10 contained in the water or PBS. This results in a clear  
solution, a portion of which, e.g., 0.2 ml, is added to  
the outside of an injured vessel, e.g., to a balloon-  
injured rat carotid artery, just prior to closing the  
wound. The resulting gel is expected to deliver the NO  
15 over a period of several hours to a few days.

#### Example 15

This example describes how a biodegradable polymer comprising an NO adduct may be prepared in situ for  
20 release of NO at a site of blood vessel injury.

In N-methyl-2-pyrrolidone containing the requisite amount of NO adduct, ATRIGEL™ (ATRIX Laboratories, Fort Collins, CO) is dissolved by stirring to result in a 50% solution of polymer by weight. Polymers which can be  
25 used include, e.g., poly(DL-lactide); 75/25 poly(DL-lactide-co-glycolide); and 50/50 poly(DL-lactide-co-caprolactone). The resulting solution gels when it comes into contact with water, e.g., in a body cavity. A portion of this solution, e.g., 0.2 ml, is injected  
30 around the area of vessel injury. After the solution gels, the drug is eluted from this system over a period of days or weeks, depending on the polymer system used.

All publications, patents, and patent applications  
35 cited herein are hereby incorporated by reference to the same extent as if each individual document were individually and specifically indicated to be


incorporated by reference and were set forth in its entirety herein.

While this invention has been described with emphasis upon preferred embodiments, it will be obvious to those of ordinary skill in the art that the preferred  
5 embodiments may be varied. It is intended that the invention may be practiced otherwise than as specifically described herein. Accordingly, this invention includes all modifications encompassed within the spirit and scope  
10 of the appended claims.

WHAT IS CLAIMED IS:

1. A method for the prophylaxis of restenosis and related disorders in a mammal, which method comprises the administration of nitric oxide by a nitric oxide delivery means, said delivery means comprising a prophylactically effective amount of a nitric oxide-releasing agent, said agent selected from the group consisting of a compound comprising a nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group and a polymer to which is bound a nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group, said agent being capable of locally releasing nitric oxide to a site at risk for restenosis in said mammal.

2. The method of claim 1 wherein said nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group is contained in a compound of the formula:




wherein J is an organic or inorganic moiety,  $\text{M}^{+x}$  is a pharmaceutically acceptable cation, where x is the valence of the cation, a is 1 or 2, and b and c are the smallest integers that result in a neutral compound.

3. The method of claim 2 wherein J is a moiety which is linked to the nitrogen of the remainder of the compound through an atom other than a carbon atom.


4. The method of claim 2 wherein the nitric oxide-releasing compound is a compound other than a salt of alanosine or dopastin.



5. The method of claim 1 wherein said nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group is contained in a compound of the formula:



10 wherein b and d are the same or different and are zero or one,  $\text{R}_1$ ,  $\text{R}_2$ ,  $\text{R}_3$ ,  $\text{R}_4$ , and  $\text{R}_5$  are the same or different and are hydrogen, a  $\text{C}_{3-8}$  cycloalkyl, a  $\text{C}_{1-12}$  straight or branched chain alkyl, benzyl, benzoyl, phthaloyl, acetyl, trifluoroacetyl, p-toluy, t-butoxycarbonyl, or 2,2,2-trichloro-t-butoxycarbonyl, and x, y, and z are the same or different and are integers from 2 to 12.

6. The method of claim 1 wherein said nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group is contained in a compound of the formula:




wherein B is  or ,

30  $\text{R}_6$  and  $\text{R}_7$  are the same or different and are hydrogen, a  $\text{C}_{3-8}$  cycloalkyl, a  $\text{C}_{1-12}$  straight or branched chain alkyl, benzyl, benzoyl, phthaloyl, acetyl, trifluoroacetyl, p-toluy, t-butoxycarbonyl, or 2,2,2-trichloro-t-butoxycarbonyl, f is an integer from 0 to 12, with the proviso that when B is the substituted piperazine moiety




then f is an integer from 2 to 12.

7. The method of claim 6 wherein B is the substituted piperazine moiety




8. The method of claim 1 wherein said nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group is contained in a compound of the formula:



wherein  $\text{R}_8$  is hydrogen, a  $\text{C}_{3-8}$  cycloalkyl, a  $\text{C}_{1-12}$  straight or branched chain alkyl, benzyl, benzoyl, phthaloyl, acetyl, trifluoroacetyl, p-toluyyl, t-butoxycarbonyl, or 2,2,2-tri-chloro-t-butoxycarbonyl,  $\text{R}_9$  is hydrogen or a  $\text{C}_{1-12}$  straight or branched chain alkyl, and  $g$  is an integer from 2 to 6.

9. The method of claim 1 wherein said nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group is contained in a compound of the formula:



wherein  $\text{R}_1$  and  $\text{R}_2$  are independently selected from the group consisting of a  $\text{C}_{1-12}$  straight or branched chain alkyl and benzyl,  $\text{M}^{+x}$  is a pharmaceutically acceptable cation, and  $x$  is the valence of the cation.



10. The method of claim 9 wherein  $R_1$  and  $R_2$  are selected so that  $R_1$  and  $R_2$  are unbranched on the alpha carbon atom or  $R_1$  and  $R_2$ , together with the nitrogen atom to which they are bonded, form a heterocyclic group.


5

11. The method of claim 10 wherein the heterocyclic group is selected from the group consisting of pyrrolidino, piperidino, piperazino and morpholino.

10

12. The method of claim 1 wherein said nitric oxide-releasing  $N_2O_2^-$  functional group is contained in a compound of the formula:

15



20

wherein M is a pharmaceutically acceptable metal, or where x is at least two, a mixture of two different pharmaceutically acceptable metals, L is a ligand different from  $(R^1R^2N-N_2O_2)$  and is bound to at least one metal,  $R^1$  and  $R^2$  are each organic moieties and are the same or different, x is an integer from 1 to 10,  $x'$  is the formal oxidation state of the metal M, and is an integer from 1 to 6, y is an integer from 1 to 18, with the proviso that y is at least 2, the ligands L are the same or different, z is an integer from 1 to 20, and K is a pharmaceutically acceptable counterion to render the compound neutral to the extent necessary.

25

30

13. The method of claim 12 wherein when M is copper, x is one, L is methanol, and y is one, then at least one of  $R^1$  or  $R^2$  is a moiety other than ethyl.

35

14. The method of claim 1 wherein said nitric oxide-releasing  $N_2O_2^-$  functional group is contained in a compound of the formula:



wherein R is a C<sub>2-8</sub> lower alkyl, phenyl, benzyl, or a C<sub>3-8</sub> cycloalkyl, any of which R groups can be substituted by one to three substituents, which are the same or different and are selected from the group consisting of halo, hydroxy, a C<sub>1-8</sub> alkoxy, -NH<sub>2</sub>, -C(O)NH<sub>2</sub>, -CH(O), -C(O)OH, and -NO<sub>2</sub>, X is a pharmaceutically acceptable cation, a pharmaceutically acceptable metal center, or a pharmaceutically acceptable organic group selected from the group consisting of a C<sub>1-8</sub> lower alkyl, -C(O)CH<sub>3</sub>, and -C(O)NH<sub>2</sub>, and y is an integer from 1 to 3, consistent with the valence of X.

15. The method of claim 1 wherein said nitric oxide-releasing N<sub>2</sub>O<sub>2</sub><sup>-</sup> functional group is contained in a compound of the formula:



wherein R<sub>1</sub> and R<sub>2</sub> are independently chosen from a C<sub>1-12</sub> straight chain alkyl, a C<sub>1-12</sub> alkoxy or acyloxy substituted straight chain alkyl, a C<sub>2-12</sub> hydroxy or halo substituted straight chain alkyl, a C<sub>3-12</sub> branched chain alkyl, a C<sub>3-12</sub> hydroxy, halo, alkoxy, or acyloxy substituted branched chain alkyl, a C<sub>3-12</sub> straight or branched chain olefinic unsubstituted or substituted with hydroxy, alkoxy, acyloxy, halo or benzyl, or R<sub>1</sub> and R<sub>2</sub> together with the nitrogen atom to which they are bonded form a heterocyclic group, and R<sub>3</sub> is a group selected from a C<sub>1-12</sub> straight chain and a C<sub>3-12</sub> branched chain alkyl which are unsubstituted or substituted by hydroxy, halo, acyloxy or alkoxy, a C<sub>2-12</sub> straight chain or a C<sub>3-12</sub> branched chain olefinic which are unsubstituted or substituted by halo, alkoxy, acyloxy or hydroxy, a C<sub>1-12</sub> unsubstituted or substituted acyl, sulfonyl, and carboxamido; or R<sub>3</sub> is a group of the formula

$-(CH_2)_n-ON=N(O)NR_1R_2$ , wherein  $n$  is an integer of 2-8, and  $R_1$  and  $R_2$  are as defined above.

16. The method of claim 15 wherein  $R_1$ ,  $R_2$  and  $R_3$  contain a moiety other than a halo or a hydroxy substituent  $\alpha$  to a heteroatom.

17. The method of claim 15 wherein the heterocyclic group is selected from the group consisting of pyrrolidino, piperidino, piperazino, and morpholino.

18. The method of claim 1 wherein said polymer is selected from the group consisting of polyolefins, polyethylenimine and derivatives thereof, polyethers, polyesters, polyamides, polyurethanes, colestipol and derivatives thereof, and biopolymers.


19. The method of claim 1 wherein said polymer is biodegradable.

20. The method of claim 1 wherein said nitric oxide delivery means is selected from the group consisting of a vascular graft prosthetic implant, stent, heart valve, suture, drug pump, catheter, self-adhering means, liposome, microparticle, microsphere, bead and disk.

21. A method for the treatment of restenosis in a mammal, which method comprises the administration of nitric oxide by a nitric oxide delivery means, said delivery means comprising an effective treatment amount of a nitric oxide-releasing agent, said agent selected from the group consisting of a compound comprising a nitric oxide-releasing  $N_2O_2^-$  functional group and a polymer to which is bound a nitric oxide-releasing  $N_2O_2^-$  functional group, said agent being capable of locally releasing nitric oxide to a site affected by restenosis in said mammal.

40

22. The method of claim 21 wherein said nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group is contained in a compound of the formula:




wherein J is an organic or inorganic moiety,  $\text{M}^{+x}$  is a pharmaceutically acceptable cation, where x is the valence of the cation, a is 1 or 2, and b and c are the smallest integers that result in a neutral compound.

23. The method of claim 22 wherein J is a moiety which is linked to the nitrogen of the remainder of the compound through an atom other than a carbon atom.

24. The method of claim 22 wherein the compound is a compound other than a salt of alanosine or dopastin.

25. The method of claim 21 wherein said nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group is contained in a compound of the formula:






wherein b and d are the same or different and may be zero or one,  $\text{R}_1$ ,  $\text{R}_2$ ,  $\text{R}_3$ ,  $\text{R}_4$ , and  $\text{R}_5$  are the same or different and are hydrogen, a  $\text{C}_{3-8}$  cycloalkyl, a  $\text{C}_{1-12}$  straight or branched chain alkyl, benzyl, benzoyl, phthaloyl, acetyl, trifluoroacetyl, p-toluyyl, t-butoxycarbonyl, or 2,2,2-trichloro-t-butoxycarbonyl, and x, y, and z are the same or different and are integers from 2 to 12.

40

41

26. The method of claim 21 wherein said nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group is contained in a compound of the formula:



wherein B is  or .

$\text{R}_6$  and  $\text{R}_7$  are the same or different and are hydrogen, a  $\text{C}_{3-8}$  cycloalkyl, a  $\text{C}_{1-12}$  straight or branched chain alkyl, benzyl, benzoyl, phthaloyl, acetyl, trifluoroacetyl, p-toluyyl, t-butoxycarbonyl, or 2,2,2-trichloro-t-butoxycarbonyl, and  $f$  is an integer from 0 to 12.


15

27. The method of claim 26 wherein B is the substituted piperazine moiety



28. The method of claim 21 wherein said nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group is contained in a compound of the formula:


25



wherein  $\text{R}_8$  is hydrogen, a  $\text{C}_{3-8}$  cycloalkyl, a  $\text{C}_{1-12}$  straight or branched chain alkyl, benzyl, benzoyl, phthaloyl, acetyl, trifluoroacetyl, p-toluyyl, t-butoxycarbonyl, or 2,2,2-tri-chloro-t-butoxycarbonyl,  $\text{R}_9$  is hydrogen or a  $\text{C}_1$ -

C<sub>12</sub> straight or branched chain alkyl, and g is an integer from 2 to 6.

29. The method of claim 21 wherein said nitric  
oxide-releasing N<sub>2</sub>O<sub>2</sub><sup>-</sup> functional group is contained in a  
compound of the formula:




wherein R<sub>1</sub> and R<sub>2</sub> are independently selected from the  
group consisting of a C<sub>1</sub>-C<sub>12</sub> straight or branched chain  
alkyl and benzyl, M<sup>+</sup><sub>x</sub> is a pharmaceutically acceptable  
cation, and x is the valence of the cation.

30. The method of claim 29 wherein R<sub>1</sub> and R<sub>2</sub> are  
selected so that R<sub>1</sub> and R<sub>2</sub> are unbranched on the alpha  
carbon atom or R<sub>1</sub> and R<sub>2</sub>, together with the nitrogen atom  
to which they are bonded, form a heterocyclic group.

31. The method of claim 30 wherein the heterocyclic  
group is selected from the group consisting of  
pyrrolidino, piperidino, piperazino and morpholino.

32. The method of claim 21 wherein said nitric  
oxide-releasing N<sub>2</sub>O<sub>2</sub><sup>-</sup> functional group is contained in a  
compound of the formula:



wherein M is a pharmaceutically acceptable metal, or  
where x is at least two, a mixture of two different  
pharmaceutically acceptable metals, L is a ligand  
different from (R<sup>1</sup>R<sup>2</sup>N-N<sub>2</sub>O<sub>2</sub>) and is bound to at least one  
metal, R<sup>1</sup> and R<sup>2</sup> are each organic moieties and are the



same or different,  $x$  is an integer from 1 to 10,  $x'$  is the formal oxidation state of the metal  $M$ , and is an integer from 1 to 6,  $y$  is an integer from 1 to 18, with the proviso that when  $y$  is at least 2, the ligands  $L$  are the same or different,  $z$  is an integer from 1 to 20, and  $K$  is a pharmaceutically acceptable counterion to render the compound neutral to the extent necessary.

33. The method of claim 32 wherein when  $M$  is copper,  $x$  is one,  $L$  is methanol, and  $y$  is one, then at least one of  $R^1$  or  $R^2$  is a moiety other than ethyl.

34. The method of claim 21 wherein said nitric oxide-releasing  $N_2O_2^-$  functional group is contained in a compound of the formula:



wherein  $R$  is a  $C_{2-8}$  lower alkyl, phenyl, benzyl, or a  $C_{3-8}$  cycloalkyl, any of which  $R$  groups may be substituted by one to three substituents, which are the same or different, and are selected from the group consisting of halo, hydroxy, a  $C_{1-8}$  alkoxy,  $-NH_2$ ,  $-C(O)NH_2$ ,  $-CH(O)$ ,  $-C(O)OH$ , and  $-NO_2$ ,  $X$  is a pharmaceutically acceptable cation, a pharmaceutically acceptable metal center, or a pharmaceutically acceptable organic group selected from the group consisting of a  $C_{1-8}$  lower alkyl,  $-C(O)CH_3$ , and  $-C(O)NH_2$ , and  $y$  is an integer from 1 to 3, consistent with the valence of  $X$ .

35. The method of claim 21 wherein said nitric oxide-releasing  $N_2O_2^-$  functional group is contained in a compound of the formula:



wherein  $R_1$  and  $R_2$  are independently chosen from a  $C_{1-12}$

straight chain alkyl, a C<sub>1-12</sub> alkoxy or acyloxy  
substituted straight chain alkyl, a C<sub>2-12</sub> hydroxy or halo  
substituted straight chain alkyl, a C<sub>3-12</sub> branched chain  
alkyl, a C<sub>3-12</sub> hydroxy, halo, alkoxy, or acyloxy  
5 substituted branched chain alkyl, a C<sub>3-12</sub> straight or  
branched chain olefinic unsubstituted or substituted with  
hydroxy, alkoxy, acyloxy, halo or benzyl, or R<sub>1</sub> and R<sub>2</sub>  
together with the nitrogen atom to which they are bonded  
form a heterocyclic group, and R<sub>3</sub> is a group selected  
10 from a C<sub>1-12</sub> straight chain and a C<sub>3-12</sub> branched chain  
alkyl which are unsubstituted or substituted by hydroxy,  
halo, acyloxy or alkoxy, a C<sub>2-12</sub> straight chain or a C<sub>3-12</sub>  
branched chain olefinic which are unsubstituted or  
substituted by halo, alkoxy, acyloxy or hydroxy, a C<sub>1-12</sub>  
15 unsubstituted or substituted acyl, sulfonyl, and  
carboxamido; or R<sub>3</sub> is a group of the formula  
-(CH<sub>2</sub>)<sub>n</sub>-ON=N(O)NR<sub>1</sub>R<sub>2</sub>, wherein n is an integer of 2-8, and  
R<sub>1</sub> and R<sub>2</sub> are as defined above.

20 36. The method of claim 35 wherein R<sub>1</sub>, R<sub>2</sub> and R<sub>3</sub>  
contain a moiety other than a halo or a hydroxy  
substituent  $\alpha$  to a heteroatom.

25 37. The method of claim 35 wherein the heterocyclic  
group is selected from the group consisting of  
pyrrolidino, piperidino, piperazino and morpholino.


30 38. The method of claim 21 wherein said polymer is  
selected from the group consisting of polyolefins,  
polyethylenimine and derivatives thereof, polyethers,  
polyesters, polyamides, polyurethanes, colestipol and  
derivatives thereof, and biopolymers.

35 39. The method of claim 21 wherein said polymer is  
biodegradable.

40. The method of claim 21 wherein said nitric oxide delivery means is selected from the group consisting of a vascular graft prosthetic implant, stent, heart valve, suture, drug pump, catheter, self-adhering means, liposome, microparticle, microsphere, bead, and disk.

41. A nitric oxide delivery means for the treatment of restenosis comprising an effective amount of a polymer to which is bound a nitric oxide-releasing  $N_2O_2^-$  functional group, said delivery means being selected from the group consisting of a vascular implant, stent, heart valve, suture, drug pump, catheter, self-adhering means, liposome, microparticle, microsphere, bead and disk.

42. The nitric oxide delivery means of claim 41 wherein said nitric oxide-releasing  $N_2O_2^-$  functional group is contained in a compound of the formula:




wherein J is an organic or inorganic moiety,  $M^{+x}$  is a pharmaceutically acceptable cation, where x is the valence of the cation, a is 1 or 2, and b and c are the smallest integers that result in a neutral compound.

43. The nitric oxide delivery means of claim 42 wherein J is a moiety which is linked to the nitrogen of the remainder of the compound through an atom other than a carbon atom.


44. The nitric oxide delivery means of claim 42 wherein the compound is a compound other than a salt of alanosine or dopastin.



45. The nitric oxide delivery means of claim 41 wherein said nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group is contained in a compound of the formula:



10 wherein b and d are the same or different and are zero or one,  $\text{R}_1$ ,  $\text{R}_2$ ,  $\text{R}_3$ ,  $\text{R}_4$ , and  $\text{R}_5$  are the same or different and are hydrogen, a  $\text{C}_{3-8}$  cycloalkyl, a  $\text{C}_{1-12}$  straight or branched chain alkyl, benzyl, benzoyl, phthaloyl, acetyl, trifluoroacetyl, p-toluyyl, t-butoxycarbonyl, or 2,2,2-  
15 trichloro-t-butoxycarbonyl, and x, y, and z are the same or different and are integers from 2 to 12.


46. The nitric oxide delivery means of claim 41 wherein said nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group  
20 is contained in a compound of the formula:




wherein B is  or .

30  $\text{R}_6$  and  $\text{R}_7$  are the same or different and are hydrogen, a  $\text{C}_{3-8}$  cycloalkyl, a  $\text{C}_{1-12}$  straight or branched chain alkyl, benzyl, benzoyl, phthaloyl, acetyl, trifluoroacetyl, p-toluyyl, t-butoxycarbonyl, or 2,2,2-trichloro-t-butoxycarbonyl, and f is an integer from 0 to 12.

35 47. The nitric oxide delivery means of claim 46 wherein B is the substituted piperazine moiety




48. The nitric oxide delivery means of claim 41 wherein said nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group is contained in a compound of the formula:



10 wherein  $R_8$  is hydrogen, a  $\text{C}_{3-8}$  cycloalkyl, a  $\text{C}_{1-12}$  straight or branched chain alkyl, benzyl, benzoyl, phthaloyl, acetyl, trifluoroacetyl, p-toluy, t-butoxycarbonyl, or 2,2,2-tri-chloro-t-butoxycarbonyl,  $R_9$  is hydrogen or a  $\text{C}_{1-}$   
 15  $\text{C}_{12}$  straight or branched chain alkyl, and  $g$  is an integer from 2 to 6.

49. The nitric oxide delivery means of claim 41 wherein said nitric oxide-releasing  $\text{N}_2\text{O}_2^-$  functional group  
 20 is contained in a compound of the formula:



30 wherein  $R_1$  and  $R_2$  are independently selected from the group consisting of a straight or branched chain alkyl and benzyl,  $\text{M}^{+x}$  is a pharmaceutically acceptable cation, and  $x$  is the valence of the cation.


35

50. The nitric oxide delivery means of claim 49 wherein  $R_1$  and  $R_2$  are selected so that  $R_1$  and  $R_2$  are unbranched on the alpha carbon atom or else  $R_1$  and  $R_2$ , together with the nitrogen atom to which they are bonded,  
 40 form a heterocyclic group.

51. The nitric oxide delivery means of claim 49 wherein the heterocyclic group is selected from the group consisting of pyrrolidino, piperidino, piperazino and morpholino.

5

52. The nitric oxide delivery means of claim 41 wherein said nitric oxide-releasing  $N_2O_2^-$  functional group is contained in a compound of the formula:




wherein M is a pharmaceutically acceptable metal, or where x is at least two, a mixture of two different pharmaceutically acceptable metals, L is a ligand different from  $(R^1R^2N-N_2O_2)$  and is bound to at least one metal,  $R^1$  and  $R^2$  are each organic moieties and are the same or different, x is an integer from 1 to 10, x' is the formal oxidation state of the metal M, and is an integer from 1 to 6, y is an integer from 1 to 18, with the proviso that when y is at least 2, the ligands L are the same or different, z is an integer from 1 to 20, and K is a pharmaceutically acceptable counterion to render the compound neutral to the extent necessary.

25

53. The nitric oxide delivery means of claim 52 wherein when M is copper, x is one, L is methanol, and y is one, then at least one of  $R^1$  or  $R^2$  is a moiety other than ethyl.

30

54. The nitric oxide delivery means of claim 41 wherein said nitric oxide-releasing  $N_2O_2^-$  functional group is contained in a compound of the formula:



35


wherein R is a  $C_{2-8}$  lower alkyl, phenyl, benzyl, or a  $C_{3-8}$  cycloalkyl, any of which R groups can be substituted by one to three substituents, which are the same or different and are selected from the group consisting of

40



halo, hydroxy, C<sub>1-8</sub> alkoxy, -NH<sub>2</sub>, -C(O)NH<sub>2</sub>, -CH(O),  
 -C(O)OH, and -NO<sub>2</sub>, X is a pharmaceutically acceptable  
 cation, a pharmaceutically acceptable metal center, or a  
 pharmaceutically acceptable organic group selected from  
 5 the group consisting of a C<sub>1-8</sub> lower alkyl, -C(O)CH<sub>3</sub>, and  
 -C(O)NH<sub>2</sub>, and y is an integer from 1 to 3, consistent  
 with the valence of X.

55. The nitric oxide delivery means of claim 41  
 10 wherein said nitric oxide-releasing N<sub>2</sub>O<sub>2</sub><sup>-</sup> functional group  
 is contained in a compound of the formula:



wherein R<sub>1</sub> and R<sub>2</sub> are independently chosen from a C<sub>1-12</sub>  
 straight chain alkyl, a C<sub>1-12</sub> alkoxy or acyloxy  
 20 substituted straight chain alkyl, a C<sub>2-12</sub> hydroxy or halo  
 substituted straight chain alkyl, a C<sub>3-12</sub> branched chain  
 alkyl, a C<sub>3-12</sub> hydroxy, halo, alkoxy, or acyloxy  
 substituted branched chain alkyl, a C<sub>3-12</sub> straight or  
 branched chain olefinic unsubstituted or substituted with  
 25 hydroxy, alkoxy, acyloxy, halo or benzyl, or R<sub>1</sub> and R<sub>2</sub>  
 together with the nitrogen atom to which they are bonded  
 form a heterocyclic group, and R<sub>3</sub> is a group selected  
 from a C<sub>1-12</sub> straight chain and a C<sub>3-12</sub> branched chain  
 alkyl which are unsubstituted or substituted by hydroxy,  
 30 halo, acyloxy or alkoxy, a C<sub>2-12</sub> straight chain or a C<sub>3-12</sub>  
 branched chain olefinic which are unsubstituted or  
 substituted by halo, alkoxy, acyloxy or hydroxy, a C<sub>1-12</sub>  
 unsubstituted or substituted acyl, sulfonyl, and  
 carboxamido; or R<sub>3</sub> is a group of the formula  
 35 -(CH<sub>2</sub>)<sub>n</sub>-ON=N(O)NR<sub>1</sub>R<sub>2</sub>, wherein n is an integer of 2-8, and  
 R<sub>1</sub> and R<sub>2</sub> are as defined above.

56. The nitric oxide delivery means of claim 55 wherein  $R_1$ ,  $R_2$  and  $R_3$  contain a moiety other than a halo or a hydroxy substituent  $\alpha$  to a heteroatom.

5 57. The nitric oxide delivery means of claim 55 wherein the heterocyclic group is selected from the group consisting of pyrrolidino, piperidino, piperazino and morpholino.

10 58. The method of claim 41 wherein said polymer is selected from the group consisting of polyolefins, polyethylenimine and derivatives thereof, polyethers, polyesters, polyamides, polyurethanes, colestipol and derivatives thereof, and biopolymers.

15 59. The nitric oxide delivery means of claim 41 wherein said polymer is biodegradable.

20 60. A method for the prophylaxis of restenosis in a mammal, which method comprises the administration of a prophylactically effective amount of a nitric oxide-releasing agent, said agent selected from the group consisting of a compound comprising a nitric oxide-releasing  $N_2O_2^-$  functional group and a polymer to which is  
25 bound a nitric oxide-releasing  $N_2O_2^-$  functional group, said agent being capable of locally releasing nitric oxide to a site at risk for restenosis in said mammal.

30 61. A method for the amelioration or therapeutic treatment of restenosis in a mammal, which method comprises the administration of a restenosis-ameliorating or therapeutically effective treatment amount of a nitric oxide-releasing agent, said agent selected from the group consisting of a compound comprising a nitric oxide-releasing  $N_2O_2^-$  functional group and a polymer to which is  
35 bound a nitric oxide-releasing  $N_2O_2^-$  functional group,

said agent being capable of releasing nitric oxide to a site affected by restenosis in said mammal.

62. The method of claim 18 wherein said polyolefin  
5 is selected from the group consisting of polystyrene, polypropylene, polyethylene, polytetrafluorethylene, polyvinylidene difluoride, and polyvinylchloride; said polyether is polyethyleneglycol; said polyester is poly(lactide/glycolide); said polyamide is nylon; said  
10 biopolymer is selected from the group consisting of a peptide, a protein, an oligonucleotide, a nucleic acid, a starburst dendrimer, and an antibody.

63. The method of claim 38 wherein said polyolefin  
15 is selected from the group consisting of polystyrene, polypropylene, polyethylene, polytetrafluorethylene, polyvinylidene difluoride, and polyvinylchloride; said polyether is polyethyleneglycol; said polyester is poly(lactide/glycolide); said polyamide is nylon; said  
20 biopolymer is selected from the group consisting of a peptide, a protein, an oligonucleotide, a nucleic acid, a starburst dendrimer, and an antibody.

64. The nitric oxide delivery means of claim 41  
25 wherein said delivery means is selected from the group consisting of a vascular graft prosthetic implant, stent, heart valve, suture, drug pump, catheter, self-adhering means, liposome, microparticle, microsphere, bead and disk.

30

65. The nitric oxide delivery means of claim 58  
wherein said polyolefin is selected from the group  
consisting of polystyrene, polypropylene, polyethylene, polytetrafluorethylene, polyvinylidene difluoride, and  
35 polyvinylchloride; said polyether is polyethyleneglycol; said polyester is poly(lactide/glycolide); said polyamide is nylon; said biopolymer is selected from the group

consisting of a peptide, a protein, an oligonucleotide, a nucleic acid, a starburst dendrimer, and an antibody.

1/6




FIG. 1




FIG. 2








FIG. 3



3/6

**FIG. 4A****FIG. 4B**

4/6

**FIG. 5A****FIG. 5B**

5/6




FIG. 6




FIG. 7

6/6




FIG. 8

## INTERNATIONAL SEARCH REPORT

Inte onal Application No  
PCT/US 95/03040A. CLASSIFICATION OF SUBJECT MATTER  
IPC 6 A61K31/785

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	J. MED. CHEM., vol. 34, no. 11, 1991 pages 3242-3247, C.M. MARAGOS ET AL. 'Complexes of NO with nucleophiles as agents for the controlled biological release of nitric oxide. Vasorelaxant effects.' cited in the application ---	
A	CANCER RES., vol. 53, no. 3, 1993 pages 564-568, C.M. MARAGOS ET AL. 'nitric oxide/nucleophile complexes inhibit the in vitro proliferation of A375 melanoma cells via nitric oxide release.' --- -/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*&\* document member of the same patent family

Date of the actual completion of the international search

4 July 1995

Date of mailing of the international search report

20.07.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+ 31-70) 340-3016

Authorized officer

Klaver, T

INTERNATIONAL SEARCH REPORT

Int ional Application No  
PCT/US 95/03040

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US,A,4 954 526 (KEEFER) 4 September 1990 cited in the application ---	
A	US,A,5 208 233 (KEEFER ET AL.) 4 May 1993 cited in the application ---	
A	US,A,5 212 204 (KEEFER ET AL.) 18 May 1993 cited in the application ---	
A	US,A,5 039 705 (KEEFER ET AL.) 13 August 1991 cited in the application ---	
A	US,A,5 155 137 (KEEFER ET AL.) 13 October 1992 cited in the application ---	
A	US,A,5 250 550 (KEEFER ET AL.) 5 October 1993 cited in the application -----	



**INTERNATIONAL SEARCH REPORT**  
Information on patent family members

International Application No  
**PCT/US 95/03040**

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-4954526	04-09-90	AT-T- 117894	15-02-95
		AU-B- 621470	12-03-92
		AU-A- 5192290	26-09-90
		CA-C- 2046910	04-04-95
		DE-D- 69016667	16-03-95
		DE-T- 69016667	01-06-95
		EP-A- 0495776	29-07-92
		ES-T- 2067022	16-03-95
		JP-T- 4505317	17-09-92
		WO-A- 9009785	07-09-90
US-A-5208233	04-05-93	US-A- 5039705	13-08-91
		AU-B- 638499	01-07-93
		AU-A- 6522690	18-04-91
		CA-A- 2066409	16-03-91
		EP-A- 0491864	01-07-92
		JP-T- 5501402	18-03-93
		WO-A- 9104022	04-04-91
US-A-5212204	18-05-93	AU-B- 637845	10-06-93
		AU-A- 6621190	16-05-91
		CA-A- 2070388	19-04-91
		EP-A- 0501975	09-09-92
		JP-T- 5504760	22-07-93
		WO-A- 9105551	02-05-91
US-A-5039705	13-08-91	AU-B- 638499	01-07-93
		AU-A- 6522690	18-04-91
		CA-A- 2066409	16-03-91
		EP-A- 0491864	01-07-92
		JP-T- 5501402	18-03-93
		WO-A- 9104022	04-04-91
		US-A- 5208233	04-05-93
US-A-5155137	13-10-92	AU-B- 649739	02-06-94
		AU-A- 8712391	15-04-92
		CA-A- 2091994	21-03-92
		EP-A- 0549704	07-07-93
		JP-T- 6501686	24-02-94
		WO-A- 9205149	02-04-92

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 95/03040

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-5155137		US-A- 5250550	05-10-93
US-A-5250550	05-10-93	US-A- 5155137	13-10-92
		WO-A- 9420415	15-09-94
		AU-B- 649739	02-06-94
		AU-A- 8712391	15-04-92
		CA-A- 2091994	21-03-92
		EP-A- 0549704	07-07-93
		JP-T- 6501686	24-02-94
		WO-A- 9205149	02-04-92